

The Mohawk Group

Direct Glue-Down Installation

Action Back

Attached Cushion

HPS Backing System

UPS Backing System

UPS Block Backing System

Weldlock

Weldlock Plus

Woven

The Mohawk Group
1975 West Oak Circle
Marietta, GA 30062
800-554-6637
www.mohawkgroup.com

Field Technical Services Department
405 Virgil Drive
Dalton, GA 30721
800-833-6954

Bigelow Commercial * Durkan Hospitality * Karastan Contract * Lees

Carpet Installation Checkoff List

1. Newly poured concrete floors generally will take 90 to 120 days to cure. Moisture should not exceed five pounds/1000sf per 24 hours as determined by a calcium chloride test per ASTM F1869, or 80% relative humidity per ASTM F2170. If the results are more than 5 lbs or higher than 80% ,do not proceed with the installation. Contact Field Services at 800.833.6954. Gypcrete or substrates with excessive dust must be cleaned, then primed with TMGs Primecoat or an approved primer, such as a latex milk additive.
2. The alkalinity or pH in a concrete slab should be between 5 and 9 for a direct glue-down installation. Should the pH be outside this range, stop and do not proceed with the installation. Contact Field Services at 800.833.6954.
3. The temperature of a concrete slab must be stabilized between 65°F and 95°F for 72 hours before and 48 hours after installation.
4. The following environmental conditions inside the building are critical for proper installation. The temperature must be between 65°F and 95°F, and the humidity between 10% and 65%, for at least 24hours before and 24 hours after installation. In addition, the adhesive and seam sealer should be stored under these conditions for at least 24 hours before installation. The installation site must be acclimated with HVAC in operation.
5. Old cut-back adhesive must be properly removed and sealed with TMG's Sureseal prior to any direct glue-down installation. See note below.
6. Carpet should be rolled out and allowed to relax for at least 24 hours prior to installation. Carpet should never be folded or creased, as this can result in permanent wrinkles.
7. Never install carpet over carpet.
8. Never cut carpet over carpet, as this can result in overpenetration of the blade and cutting loops on the lower carpet.
9. Carpet should be protected from heavy traffic and construction dust with a non-staining building material paper, such as "kraft" paper. Never use plastic sheeting as it will trap moisture and prevent proper curing of the adhesive. Plastic may also leave residues that can result in rapid soiling after removal.
10. Furniture placement and heavy traffic should be avoided for at least 24 hours after a direct glue-down installation. Furniture and heavy equipment concentrated pressure, and movement over unprotected carpet can cause adhesive breakdown. This can result in buckling and/or wrinkling. It is strongly recommended that plywood or masonite boards be placed over the carpet during the move-in phase to spread the concentrated weight of furniture and heavy equipment.

Please Note: Asbestos-containing floor tiles, any adhesive possibly containing asbestos, or other asbestos-containing floor coverings require special preparation, handling, and removal procedures. Consult the appropriate local or state authorities or the Resilient Floor Covering Institute before disturbing any suspected asbestos-containing material.

Required Tools And Materials

The following items may be purchased from a local carpet workroom supplier.

- | | |
|---|-------------------|
| 1. NuBroadlok Adhesive | 9. Straight Edges |
| 2. NuBroadlok Seam Sealer | 10. Razor Knives |
| 3. NuBroadlok Edge Sealer | 11. Dead Man |
| 4. Cushion back cutter or top cutter | 12. Hammer |
| 5. 1/8" x 1/8" x 1/8" U-notched trowel
or 1/8" x 1/8" x 1/16" V-notched trowel | 13. Stay Nails |
| 6. 50 to 75 lb. roller | 14. Dry Line |
| 7. Mini or Crab Stretcher and Power Stretcher | 15. Chalk Line |
| 8. Knee Kicker | 16. Tape Measure |

Pile Direction

All full-width carpets have an arrow on the back running approximately 2 feet from the selvage along one side of the carpet or a selvage marker to indicate pile direction. When seaming, the pieces of carpet should be joined with the arrow running in the same direction on each breadth. All cut carpet used as fill pieces should be marked to indicate pile direction before the arrows are removed.

Recommended Cutting Methods

Tufted and Woven carpets should be cut between the rows using a top cutter. In all cut/loop and loop constructions, care must be taken to ensure that no loops are cut.

Lengthwise Cuts

Bend the carpet along the length to separate the rows and expose the backing yarns. Part or trace the pile with a screwdriver along the length of the proposed cut. Start the cut by making a small incision on the edge with a carpet knife. Insert the top cutter between the backing yarns and cut along the face of the carpet. The top cutter should always be inserted so that the blade is close to the seam edge.

Please Note: Seam Sealer or Edge Sealer must be used on all seams.

Widthwise Cuts (Woven Goods)

Follow the same procedure as for lengthwise cuts, inserting the top cutter with the blade close to the seam edge. All cut edges must be sealed by pressing a thin coating of NuBroadlok Edge Sealer into the base of the pile and backing.

Please Note: Edge Sealer must be used on all cuts immediately.

Widthwise Cuts (Tufted)

All widthwise cuts must be made with a top cutter and straight edge following a pattern from point to point. Trim with the blade closest to the seam edge; holding the cutter slightly away from the seam edge at no more than a 5 degree angle, so as to cut slightly more backing material than face yarn.

Pattern Matching

It must be understood that carpet is a textile and cannot be made to exact specifications. All patterned carpet is subject to certain manufacturing tolerances, therefore a perfect pattern match cannot be guaranteed. However, a match should be achievable by stretching the short side out to meet the long side. Tolerances for patterned carpet are:

Bow: 1-1/2 inches across the 12-foot width

Skew (bias): 1-1/2 inches across the 12-foot width

Pattern elongation: 1-1/2 inches in 12 feet along the length

Pattern Elongation

All rolls should be dry-laid and the pattern repeat measured to establish the correct roll sequence. The longest pattern must be installed first, then the next longest, etc. This allows the shorter pattern to be stretched to the longer pattern, and keeps the closest pattern repeats together. After the roll sequence is established, glue half the long pattern and half the shorter pattern lengthwise. Stretch the shorter pattern to match the longer pattern by starting the center of the seam and stretching toward the ends. Stay nail will be needed to secure the pattern match as the adhesive sets.

Corrective Steps for Bow and Skew

For direct glue-down installations, make a cut across the patterns at one end. Then apply the adhesive using the proper trowel. Push the short corners to the wall and stretch the excess carpet created by the bow or skew to the opposite wall using a power stretcher and crab stretcher. Use stay nails to hold the pattern in place until the adhesive sets. Follow this procedure throughout the installation. In large rooms start in the center of the seam correcting the bow & skew with a stretcher or mini stretcher. A dry line should be placed along the pattern for reference.

If you are having trouble matching a pattern, STOP at once and call the hotline number, 800-833-6954.

Please Note: Pattern installation instructions and diagrams are shipped in each roll of carpet.

Applying Approved Adhesive

NuBroadlok is the only adhesive approved for use in direct glue-down installations. The use of NuBroadlok Adhesive is vital to ensure optimum results. Applying an improper adhesive can result in an installation failure for which TMG cannot be held responsible. To make certain that the proper amount of adhesive is transferred to the back of the carpet, a 1/8" x 1/8" x 1/8" U-notched trowel or 1/8" x 1/8" x 1/16" V-notched trowel must be used. This will result in a spread rate of approximately 8 - 10 yards per gallon.

Proper open time is critical for the adhesive to develop the proper tack. Open time will usually range from 10 to 30 minutes but should be evaluated in a small area before proceeding with the installation. Allow the adhesive to remain open long enough to develop tack, however not too tacky that the pattern cannot slip to make a proper match.

General Installation Procedures

1. Make sure that the pile-lay runs in the same direction. Check starting wall for squareness, allowing for an off-square wall. Strike a chalk line the entire length of the area where the seam falls.
2. Place two lengths in the proper position for installing, and trim selvages. Line up the seam edges with the chalk line, making sure they are perfectly flat and tension free.
3. Fold or roll both widths back 3 feet from the seam area for the entire length of the carpet.
4. Spread NuBroadlok Adhesive from the approximate center toward each end, using a 1/8" x 1/8" x 1/8" U-notched trowel or 1/8" x 1/8" x 1/16" V-notched trowel and steady, even strokes. When sufficient floor area has been covered with NuBroadlok, wait until the adhesive has reached the appropriate tacky stage before dropping the first breadth of carpet into place. Apply a thin coating of NuBroadlok Seam Sealer to the seam edge of the first breadth. Follow this procedure for each succeeding breadth at the seam. If edge sealer is used then both edges must be sealed by pressing a thin coating of NuBroadlok Edge Sealer to both seam edges into the base of the pile and backing. The sealer should be dried completely before making seam. Drop or roll the second breadth into position, and fit the seam in tightly using a knee kicker if necessary. Roll looseness and air bubbles away from the seam.

Please Note: Seam Sealer or edge sealer must be used on all seams.

5. The remaining portion of the first breadth can now be folded or rolled back from the floor. Apply NuBroadlok to the floor; wait until the adhesive has reached the proper tacky stage before dropping the carpet into place. Be sure to have enough people spreading the adhesive so that, after the floor is covered with adhesive, each breadth is in place within the determined period of open time.
6. Roll or fold back the dry portion of the second breadth toward the seam, spread the NuBroadlok, and place the carpet to 3 feet from where the next seam will fall.
7. Be sure to roll out looseness and air bubbles as the carpet is put in place. Repeat above procedures on continuing breadths. To trim the carpet at the wall, use a razor-blade knife or suitable wall trimmer.
8. Roll completed installation with a 50 to 75 lb. roller in both length and width. This will allow the adhesive to penetrate the carpet back properly.

Double-Bond Procedures

Additional double-bond instructions are available upon request.

This information, offered as a customer service, is based on TMG's engineering tests and field experience. It is intended for installers with professional experience, to be used at their discretion and risk. TMG does not guarantee results and assumes no liability in connection with these installation instructions.

Please Note:

The use of TMG's branded adhesives are required to ensure optimum results and are the only approved adhesives that TMG will warrant. Failure to use TMG's branded adhesives can result in warranties being null and void.